



## SURFACE CURE A

### DESCRIPTION

SURFACE-CURE A- WATERBASED CURING COMPOUND is a Class D, Type 1 curing compound for use on new concrete that facilitates maximum moisture retention through 28 days curing period to maximise concrete strength & durability.

SURFACE CURE A can also be generally classed as a Class Z, Type 1 it comes back to interpretation of definitions.

The polymer used is a synthetic acrylic and can fit in both class descriptions.

SURFACE-CURE A, cures, seals, and hardens the surface of new concrete, providing increased strength and durability and improved resistance to chemicals and surface dusting, when applied by the correct method and at the recommended application rate.

The dried film, which is not particularly obvious and has minimal darkening on exposure to sunlight.

SURFACE-CURE A is based on an acrylic resin combined with other additives.

### USE

Mainly used on freshly laid concrete floors, carparks, warehouses, bridge ramparts etc.

Also used for curing vertical concrete areas immediately after the stripping of forms to assist strength development, improve chemical resistance, etc.

### ADVANTAGES OF USE

- Environmentally acceptable.
- low Solvent - water based (not classed as Hazardous or Dangerous) Low VOC
- Complies with GREEN STAR- OFFICE DESIGN V3 IEQ-13 (<200g/L TVOC)
- Low odour.
- No ventilation requirement.
- No stringent safety requirements.
- Fast dry
- Efficient curing of the concrete assists the Development of strength, abrasion resistance and durability.

- Reduces the likelihood of cracking or dusting at the surface.
- Easy to use, eliminates messy water curing or polythene film.

### STANDARDS COMPLIANCE

SURFACE CURE A conforms to AS 3799-1998: liquid membrane forming curing compounds for concrete, having a Moisture Retention Efficiency of 94%. Test certificates are available on request.

SURFACE CURE A conforms to R.M.S. specification R80 (as Class Z), R82, R83, R84. & is listed on TMR as an approved product.

### DESIGN & SPECIFICATION DETAIL

The coating should be applied in a single coat to achieve the required dry film thickness sufficient to achieve the correct curing properties, SURFACE CURE A must be applied on to the substrate at the coverage rates recommended.

### CONCRETE CURING COMPOUND

All designated areas are to have a liquid curing compound applied to the freshly finished concrete.

The curing compound will be based on an acrylic resin, comply with AS3799.

Such a material is SURFACE CURE A as supplied by Chemical House.

The curing compound is to be applied in accordance with the manufacturer's application instructions.

SURFACE CURE A should be evenly sprayed over the freshly laid concrete as soon as possible after final trowelling.

Ideally SURFACE CURE A should be applied as soon as the surface bleed water has evaporated.

### LIMITATIONS

Certain adhesives for vinyl tiles, or other types of resilient flooring, and paints of an approved grade may be applied to concrete coated with SURFACE CURE A.

It is important however that the concrete should be thoroughly cured prior to such application, and that a test area has been completed for approval.





# Technical Data Sheet

May-26

Cement based renders and toppings should not be applied over SURFACE CURE A.

First remove the SURFACE CURE A by sand blasting or scabbling to provide a mechanical key.

The life of SURFACE CURE A will depend on traffic conditions to which it has been subjected; therefore, apply reviving coats as required.

The bond of SURFACE CURE A is likely to fail if the product is applied to concrete or masonry substrates subject to back water pressure, and/or where extraneous salt particles are carried from the substrate to the interface by vapour or condensation.

Chemicals to which SURFACE CURE A is not resistant include oxidising agents, such as sodium hypochlorite, bromine water and sulphur dioxide.

SURFACE CURE A is also not resistant to concentrated acetic acid, concentrated phosphoric acid, concentrated nitric acid, chromic acid, concentrated ammonia, animal fats and oils, synthetic oils such as brake fluid and some transmission fluids, vegetable oils and higher fatty acids such as oleic acid plus the following solvent types: aromatic hydrocarbons, esters, ketones and chlorinated solvents.

## USE

Mix prior to use.

Ensure SURFACE-CURE A is homogeneous.

SURFACE-CURE A contains no fugitive dye so care should be exercised to ensure a uniform application is achieved.

Calculate area to be treated, pre-measure the volume of SURFACE-CURE A.

Apply one full coat forming a continuous film at a rate of 5m<sup>2</sup>/L. wet on wet, as required to obtain the necessary application rate or use the volume. Ensure there are no misses.

## APPLICATION EQUIPMENT

Low pressure spray (preferred) or soft 10-15mm nap roller.

## DRYING TIME

Approximately 1 to 2 hours at 25degC.

After this time, the SURFACE-CURE A will be shower resistant and will resist re-emulsification and consequential removal.

This feature will help diminish the potential for wash away by rain within 8 hours of application.

## TECHNICAL DATA

<b>COVERAGE</b>	5m <sup>2</sup> per litre (0.2L/m <sup>2</sup> ) as supplied
<b>CLEAN UP</b>	Xylene or Easi-Orange
<b>FIRST AID, SAFETY &amp; STORAGE</b>	Refer to Material Safety Data sheet.
<b>PACKS</b>	20L, 200L, 1000 (IBC)



SURFACE CURE A - TDS MAY 2026

This Product Data Sheet (PDS) summarises our best knowledge of the product, including how to use and apply the product based on the information available at the time. You should read this PDS carefully and consider the information in the context of how the product will be used, including in conjunction with any other product and the type of surfaces to, and the way, the product will be applied. Our responsibility for products sold is subject to our standard terms and conditions of sale. Chemical House does not accept any liability either directly or indirectly for any losses suffered in connection with the use or application of the product whether in accordance with any advice, specification, recommendation, or information given by it.

## CHEMICAL HOUSE

9 Production Avenue, Molendinar  
Queensland, 4214 Australia  
Ph: +61 7 5594 0344